



### MIROCAT PC 3241 Clear Sealer

MIROCAT PC 3241 is a single pack, pre-catalysed sanding sealer that provides an excellent base for a range of Mirotone topcoats. The rapid drying time and excellent free sanding ensure reduced down time between coats, whilst the excellent build reduces the number of topcoats required.

#### Product Advantages

- High build provides improved hold up and reduces the number of coats required.
- Easy to use, achieve an excellent finish with minimal effort.
- Fast drying allows early sanding which minimises production time.

#### Typical Applications

Interior use only. Ideal for domestic furniture, children's toys and furniture, picture frames, musical instruments, joinery and antique restoration.

#### Product Properties

Build:	High
Sandability:	Excellent
Vertical Hold Up:	Very Good
Solvent Resistance:	Good
Water Resistance:	Good
Levelling & Flow:	Excellent
Sink Back:	Minimal

#### Typical Properties

Colour:	Turbid in can, dries clear
Gloss:	N/A

**Coverage:** 6 m<sup>2</sup> per litre at 150 micron wet film build. This is dependent on the application equipment / gun set up and the article being coated.

**Thinning:** Thin up to 10% with MIROSOL 1222 or 1220 (Fast), 1294 (Medium)

**Application Viscosity:** 50-60 seconds BS4 Flow Cup at 25°C.

**Wet Film Thickness (WFT):** 150-200 microns per coat.

#### Application Methods:

Suction Gun:	Use 1.5 to 2mm (59-79 thou) orifice with 350-400kpa (50-55 psi).
Pressure Pot:	Use 1.5 to 2mm (59-79 thou) orifice with pressure pot air-cap. Gun pressure 350-400kpa (50-55 psi) and a pot pressure of 45kpa (6 psi) max.
Airless Spray:	Use 0.23 to 0.33mm (9-13 thou) orifice, 15cm fan (dependent on job) with regulated pump pressure of 350-400kpa (50-55 psi).
Air Mix Guns:	Settings similar to airless spray with the air-assisted regulator pressure at 70-90kpa (10-15psi).

**Drying:** Dust Free: 15-20 minutes  
Touch Dry: 25-30 minutes  
Sanding: 2-3 hours  
Topcoat: Within 24 hours of sanding  
Block Stacking: 24 hours

*Low temperatures and heavy wet film thickness will retard drying times.*

**Recommended Topcoats:** MIROCAT PC 3210 Clear Topcoat  
MIROCAT PC 3220 Clear Topcoat  
MIROTHANE PU 5588 Clear Topcoat

**Application Equipment Clean Up:** Clean all equipment using MIROSOL 1222 Thinner

**Shelf Life:** 24 months

**Packaging:** 4 ltrs, and 20 ltrs

**Refer to the MIROCAT PC Product Information Guide for more information.**

### **Health & Safety**

Before handling, refer to the Material Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.

---

**Mirotone Pty Ltd Australia (Head Office)**  
ABN 40 000 041 136  
21 Marigold Street,  
Revesby NSW 2212 Australia  
P +61 2 9795 3700 F +61 2 9771 3601  
sales@mirotone.com.au

**Mirotone (NZ) Ltd New Zealand (Head Office)**  
32 Cryers Road, East Tamaki  
Auckland 2013 New Zealand  
P 0800 34 64 74 F 0800 34 64 34  
information@mirotone.co.nz

**Mirotone (Thailand) Co., Ltd**  
83 Moo 4, Poochaosamingprai Rd,  
Samrong Klang, Prapradaeng,  
Samutprakam, 10130, Thailand  
P +66 2 754 4451 F +66 2 754 4450

**[www.mirotone.com](http://www.mirotone.com)**