

## MIROLAC NC 3130 Pigmented Undercoat

MIROLAC NC 3130 is a user friendly, single pack, pigmented undercoat for internal wood and medium density fireboard (MDF). It is fast drying with excellent sanding properties.

### Product Advantages

- Easy to sand, powders easily reducing sanding time.
- Fast drying enables increased production throughput
- Minimises the risk of wax extraction when applied over MDF and HDF.
- Single pack, no pot life issues to manage
- Formaldehyde free, safer for the applicator, zero formaldehyde emissions in rooms in which articles are installed.
- Use up left over MIROLAC NC 3150 topcoat by adding to MIROLAC NC 3130 to create your own tinted undercoats.

### Typical Applications

Interior use only. Ideal for domestic furniture, internal doors, children's toys and furniture and built in wardrobes.

### Product Properties

Build:	Good
Sandability:	Good
Vertical Hold Up:	Good
Solvent Resistance:	Good
Water Resistance:	Good
Levelling & Flow:	Very Good
Sink Back:	Minimal

### Typical Properties

Colour:	White, may be tinted
Gloss:	N/A

**Coverage:** 6 m<sup>2</sup> per litre at 150 micron wet film build. This is dependent on the application equipment / gun set up and the article being coated.

**Thinning:** Thin 25-40% with MIROSOL 1222 or 1220 (Fast) and 1294 (Medium)

**Application Viscosity:** 45-55 seconds BS4 Flow Cup at 25°C.

**Wet Film Thickness (WFT):** 100-150 microns per coat.

**Application Methods:**

Suction Gun: Use 1.5 to 2mm (59-79 thou) orifice with 350-400kpa (50-55 psi).  
Pressure Pot: Use 1.5 to 2mm (59-79 thou) orifice with pressure pot air-cap. Gun pressure 350-400kpa (50-55 psi) and a pot pressure of 45kpa (6 psi) max.  
Airless Spray: Use 0.23 to 0.33mm (9-13 thou) orifice, 15cm fan (dependent on job) with regulated pump pressure of 350-400kpa (50-55 psi).  
Air Mix Guns: Settings similar to airless spray with the air-assisted regulator pressure at 70-90kpa (10-15psi).

**Drying:** Dust Free: 5-10 minutes  
Touch Dry: 10-15 minutes  
Sanding: 30-60 minutes  
Topcoat: Within 24 hours of sanding  
Block Stacking: 24 hours

*Low temperatures and heavy film thickness will retard drying times.*

**Recommended Topcoats:** MIROLAC NC 3150 Pigmented Nitrocellulose Topcoat

**Application Equipment Clean Up:** Clean all equipment using MIROSOL 1222 or MIROSOL 1215 Gunwash

**Shelf Life:** 24 months

**Packaging:** 20 ltr

**Refer to the MIROLAC NC Product Information Guide for more information.**

**Health & Safety**

Before handling, refer to the Material Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.

---

**Mirotone Pty Ltd Australia (Head Office)**  
ABN 40 000 041 136  
21 Marigold Street,  
Revesby NSW 2212 Australia  
P +61 2 9795 3700 F +61 2 9771 3601  
sales@mirotone.com.au

**Mirotone (NZ) Limited New Zealand**  
32 Cryers Road, East Tamaki  
Auckland, 2013, New Zealand  
P 0800 34 64 74 F 0800 34 64 34  
information@mirotone.co.nz

**Mirotone (Thailand) Co., Ltd**  
83 Moo 4, Poochaosamingprai Rd,  
Samrong Klang, Prapradaeng,  
Samutprakam, 10130, Thailand  
P +66 2 754 4451 F +66 2 754 4450

**[www.mirotone.com](http://www.mirotone.com)**