



MIROTHANE PU 5650 Pigmented Topcoat

MIROTHANE PU 5650 is a user friendly, two pack, fast cure polyurethane topcoat. It has been formulated to have superior resistance to water, general household contaminants, marring and scuffing. Available in a superb full gloss with excellent flow, levelling and distinctiveness of image (DOI) and a fast drying, easy to apply satin finish.

Product Advantages

- Available in an extensive colour range or tintable to a colour sample
- Excellent flow and levelling results in a smooth even finish.
- With the application of the recommended undercoat or primer may be applied over wood, MDF, melamine, glass, metal and plastic.

Typical Applications

Interior use only for example interior doors, kitchen & bathroom cabinets, commercial joinery and wall panelling and domestic furniture.

With the appropriate primers may be used to topcoat glass, plastic and metal.

Product Properties

Build:	Very Good
Sandability:	Good
Vertical Hold Up:	Good
Solvent Resistance:	Excellent
Water Resistance:	Excellent
Levelling & Flow:	Excellent
Sink Back:	Minimal

Typical Properties

Colour:	White & tinted colours
Gloss:	Satin & Full Gloss

Coverage: 8m² per litre at 125 micron wet film build. This is dependent on the application equipment/gun set up and the article being coated.

Mixing Ratio (by volume):

Satin:	PU 5747 RFU Hardener	1A:1B	30% Gloss
	PU 5728 Fast Cure Hardener	2A:1B	40-50% Gloss
		3A:1B	20% Gloss
	PU 5735 Fast-Med Cure Hardener	2A:1B	50-60% Gloss
		3A:1B	25-35% Gloss
Full Gloss:	PU 5780 RFU Hardener	1A:1B	
	PU 5757 Medium Cure Hardener	2A:1B	
Pot Life:	Satin -	> 8 hours	
	Full Gloss -	> 2 – 8 hours	

Pot life varies significantly with ambient temperature, humidity and the quantity mixed. Pot life is longer at lower temperatures and shorter at higher temperatures. The larger the quantity mixed, the shorter the pot life will be. Only mix the quantity required for the job.

Thinning: Satin – Thin 40-55% with MIROSOL 1217 (Fast), 1265 (Medium), 1266 (Med-Slow) when using high solids Part B.
When using Ready For Use (RFU) Part B's thin 30-40%.
Full Gloss – thin up to 25% with MIROSOL 1260 or 1266

MIROSOL 1281 Matt Promoter may be added to MIROTHANE PU 5650 Satin at an addition rate of 30-40% to achieve an approximate gloss level of 10-15%.

In order to maintain consistency of colour and gloss during a job or repeat jobs of the same colour, it is critical to use the same Part B Hardener and thinner throughout. To speed up dry time add up to 3% MIROTHANE PU 5795 Accelerator.

Application Viscosity: 17-20 seconds BS4 Flow Cup at 25°C.

Wet Film Thickness (WFT): 125 - 150 microns per coat.

Application Methods:

Suction Gun: Use 1.5 to 2mm (59-79 thou) orifice with 350-400kpa (50-55 psi).
Pressure Pot: Use 1.5 to 2mm (59-79 thou) orifice with pressure pot air-cap. Gun pressure 350-400kpa (50-55 psi) and a pot pressure of 45kpa (6 psi) max.
Airless Spray: Use 0.23 to 0.33mm (9-13 thou) orifice, 15cm fan (dependent on job) with regulated pump pressure of 350-400kpa (50-55 psi).
Air Mix Guns: Settings similar to airless spray with the air-assisted regulator pressure at 70-90kpa (10-15psi).

Drying:
Dust Free: 8 minutes
Touch Dry: 30 minutes
Sanding: 100 minutes (depending upon temperature)
Topcoat: Within 24 hours of sanding
Block Stacking: 24 hours

Temperatures below 16°C will retard the curing reaction of the product. Drying time is also affected by wet film thickness, the higher the WFT the slower the rate of reaction and the longer the dry time.

Recommended Undercoats: MIROLAC NC 3125 (for subdued gloss level only)
MIROTHANE PU 5626 or 5631
Metal Primers: MIROKEY VY 6615 Etch Primer
MIROLON ZP 6930 Rapid Dry Zinc Phosphate Primer
MIROTHANE PU 5629 2K Metal Primer

Application Equipment Clean Up: Clean all equipment using MIROSOL 1222 Thinner.

Shelf Life: MIROTHANE PU Part A & Part B – 12 months

Packaging: MIROTHANE PU Part A – Available in 1,4 and 16 litres

Refer to the MIROTHANE PU Product Information Guide for more information.

Health & Safety

Before handling, refer to the Material Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.

Mirotone Pty Ltd Australia (Head Office)
ABN 40 000 041 136
21 Marigold Street,
Revesby NSW 2212 Australia
P +61 2 9795 3700 F +61 2 9771 3601
sales@mirotone.com.au

Mirotone (NZ) Ltd New Zealand (Head Office)
32 Cryers Road, East Tamaki
Auckland 2013, New Zealand
P 0800 34 64 74 F 0800 34 64 34
information@mirotone.co.nz

Mirotone (Thailand) Co., Ltd
83 Moo 4, Poochaosamingprai Rd,
Samrong Klang, Prapadaeng,
Samutprakam, 10130, Thailand
P +66 2 754 4451 F +66 2 754 4450

www.mirotone.com